

NO.WRD/WDXI/SDIII/TECH/W.F.02/2022/2022-23/68

. Dated:-14/12/2022

GOVERNMENT OF GOA
SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Improvement to nallah in Sy.No.21/4 and 22/3 in V.P. Querim in Priol Constituency.

SAMPLE SENT BY: AE, SD IV, WD XI, WRD, Ponda- Goa.

NAME OF THE AGENCY

TESTING PERIOD

28 days.

REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	REQUIRED STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
1.1	F.02/11/2022						115.56		No. WRD/WD XI/SD IV/
	F.02/12/2022	12/10/2022	9/11/2022	For Foundation RHS	1.3.6	100 kg/cm2	106.67	111.11	F.CF/ 343 /2022-23.
	F.02/13/2022						111.11		DATED: 02-11-2022.
1.2	F.02/14/2022						115.56		
	F.02/15/2022	12/10/2022	9/11/2022	For Foundation RHS	1.3.6	100 kg/cm2	111.11	112.59	do
	F.02/16/2022						111.11		
2.1	F.02/17/2022						106.67		
	F.02/18/2022	14-10-2022	11/11/2022	For Foundation RHS	1.3.6	100 kg/cm2	102.22	106.67	do
	F.02/19/2022						111.11		
2.2	F.02/20/2022						115.56		
	F.02/21/2022	14-10-2022	11/11/2022	For Foundation RHS	1.3.6	100 kg/cm2	97.78	105.19	do
	F.02/22/2022						102.22		
3.1	F.02/23/2022						106.67		
	F.02/24/2022	15-10-2022	12/11/2022	For Foundation RHS	1.3.6	100 kg/cm2	111.11	108.15	do
	F.02/25/2022						106.67		
3.2	F.02/26/2022						106.67		
	F.02/27/2022	15-10-2022	12/11/2022	For Foundation RHS	1.3.6	100 kg/cm2	111.11	109.63	do
	F.02/28/2022						111.11		
4.1	F.02/29/2022						102.22		
	F.02/30/2022	17-10-2022	14-11-2022	For Foundation LHS	1.3.6	100 kg/cm2	106.67	105.19	do
	F.02/31/2022						106.67		
4.2	F.02/32/2022						111.11		
	F.02/33/2022	17-10-2022	14-11-2022	For Foundation LHS	1.3.6	100 kg/cm2	106.67	106.67	do
	F.02/34/2022						102.22		

JUNIOR ENGINEER.

ASSISTANT ENGINEER

GOVERNMENT OF GOA

SD III (QC) , WRD, GOGAL, MARGAO- GOA.

NAME OF THE WORK: Improvement to nallah in Sy.No.21/4 and 22/3 in V.P. Querim in Priol Constituency.

SAMPLE SENT BY: AE, SD IV, WD XI, WRD, Ponda- Goa.

NAME OF THE AGENCY

TESTING PERIOD

28 days.

REPORT NO	SAMPLE NOS.	CASTING DATE	TESTING DATE	LOCATION OF SAMPLE	MIX PROPOTION	REQUIRED STRENGTH	Comp sth in Kg/cm2	Avg. Comp Kg/cm2	LETTER No / DATED
5.1	F.02/35/2022						115.56		No. WRD/WD XI/SD IV/ F.CF/ 343 /2022-23. DATED: 02-11-2022.
	F.02/36/2022	18-10-2022	15-11-2022	For Foundation LHS	1.3.6	100 kg/cm2	120.00	114.08	
	F.02/37/2022						106.67		
5.2	F.02/38/2022						115.56		
	F.02/39/2022	18-10-2022	15-11-2022	For Foundation LHS	1.3.6	100 kg/cm2	115.56	112.60	do
	F.02/40/2022						106.67		
6.1	F.02/41/2022						106.67		
	F.02/42/2022	19-10-2022	16-11-2022	For Foundation LHS	1.3.6	100 kg/cm2	111.11	111.11	do
	F.02/43/2022						115.56		
6.2	F.02/44/2022						111.11		
	F.02/45/2022	19-10-2022	16-11-2022	For Foundation LHS	1.3.6	100 kg/cm2	115.56	112.59	do
	F.02/46/2022						111.11		
7	F.02/47/2022						102.22		
	F.02/48/2022	25-10-2022	22-11-2022	Horizontal band	1.3.6	100 kg/cm2	106.67	103.70	do
	F.02/49/2022						102.22		
8	F.02/50/2022						106.67		
	F.02/51/2022	31-10-2022	28-11-2022	Horizontal band	1.3.6	100 kg/cm2	102.22	105.19	do
	F.02/52/2022						106.67		

JUNIOR ENGINEER.

ASSISTANT ENGINEER