

**GOVERNMENT OF GOA
QUALITY CONTROL LABORATORY
WATER RESOURCES DEPARTMENT**

Test Report No.: WRD/Q.C./F.6-4/Aggr-T- 287,288/Lab/06/2023-24 **Dated:-**04/04/2023.

Laboratory: Bicholim-Goa

Sand –T:- 5371. **Cement-T:-** 1428.

Sub Div: V (QC)/WRD/Bicholim Goa.

Sub:- Construction of Siolim Minor-I and field channels of OL-1, OL-2, OL-3 and OT of Kamurlim Minor-2 of LBMC of TIP at Village Siolim in Bardez Taluka.

Ref to requisition No:- SDI/WDVIII/WRD/WF.25/2022-23/238 **Dated :-** 29/03/2023

Qty. Received: 1 bags each **Date of Receipt:-** 29/03/2023 **Tested on:-** 30,31/03/2023 & 01,03/04/2023. **Ref to Specification:** CPWD 2009, Vol. I&IS:4031-4-1968

Sample:Sand,20mm, **O.S. NO:-** 1035,1036,567,540/SS. **Lab. Sample No :-** 6624 to 6627 **Tested by:-** Mrs. R.R. Kadam A.E. & Mrs. S. B. Naik Shirodkar J.E.

12.5mm size Aggr, and Cement

R E P O R T 01 OF 01

Sr. No.	Description of sample	Tested for	Results	Max. /Min. value permissible	Remarks
1.	20.00 mm Size Aggregate:	Particle size distribution:	It is single sized aggregate of 20 mm nominal size.	(Qty. rep. – --m ³)	
2.	12.5 mm Size Aggregate:	Particle size distribution:	It is not single sized aggregate of 12.5 mm nominal size.	(Qty. rep. – -- m ³)	
REMARK: After blending 20 mm aggregate with 12.5 mm aggregates at the ratio of 1:1 by weight; it is satisfying the required criteria for graded aggregate of 20 mm nominal size.					
3.	Coarse Sand: (L.S.No.6626)	i) Silt & Clay by S.A. method ii) Silt by sedimentation iii) Fineness Modulus iv) Grading Zone	: - 4.40% : - 4.65% : - 2.24% : - III		
REMARK: The observed results are within the permissible limits of the Coarse sand.					
4.	Cement: JK Cement, bearing IS:269 Ordinary Portland cement, Manuf. date: W-11,M-03,Y-2023 CM/L = 0003401033 Qty. rep. –.	i) Fineness of Cement ii) Consistency of cement iii) Initial Setting Time iv) Final Setting Time	: - 1.03% : - 31.50% : - 165 minutes : - 270 minutes	----- (It should not be more than 10%) (It should be in the neighborhood of 35%) ---- (It should not be less than 30 minutes) -- (It should not be more than 600 minutes)	
To be used for - REMARK: The observed results are within the permissible limit for Ordinary Portland cement.					

Copy to:1. The Assistant Engineer, SDI, WDVIII, WRD, Karaswada, Bardez– Goa.

2. Copy Submitted to The Superintending Engineer, CPO, WRD, Porvorim – Goa for kind information.

3. Copy Submitted to The Executive Engineer, WDVIII, WRD, Karaswada, Bardez– Goa.

4. Q.C. Lab file 5. Bill File.

Junior Engineer

Assistant Engineer